

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	Impurities
Aluminium Bronze IS:305-1981												
AB-1	Rem.	0.1	0.05	0.5	1.5-3.5	1		8.5-10.5	1	0.25		0.3
AB-2	Rem.	0.1	0.05	0.5	4.5 - 5	4.-5.5		8.8-10	1.5	0.10		0.3
IS:3091-1963												
Al.Bronze	Rem.				4-5			9-11	0.1- 0.5			
IS:8631-1977												
Grade-1	Rem.	0.1	0.05	0.5	4-5.5	4-5.5		8.8-10	1	0.1		