

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
High Tensile Brass													
C66700	68.5-71.5		0.07	Rem.	0.1				0.8-1.5				
C66800	60-63	0.3	0.5	Rem.	0.35	0.25		0.25	2-3.5	0.5-1.5			
C66900	62.5-64.5		0.05	Rem.	0.25				11.5-12.5				
C66950	Rem.		0.01	14-15	0.5			1-1.5	14-15				
C67000	63-68	0.5	0.2	Rem.	2-4			3-6	2.5-5				
C67300	58-63	0.3	0.4-3	Rem.	0.5	0.25		0.25	2-3.5	0.5-1.5			
C67400	57-60	0.3	0.5	Rem.	0.35	0.25		0.5-2	2-3.5	0.5-1.5			
C67420	57-58.5	0.35	0.25-0.8	Rem.	0.15-0.55	0.25		1-2	1.5-2.5	0.25-0.7			
C86100	66-68	0.2	0.2	Rem.	2-4			4.5-5.5	2.5-5				
C86200	60-66	0.2	0.2	22-28	2-4	1		3-4.9	2.5-5				
C86300	60-66	0.2	0.2	22-28	2-4	1		5-7.5	2.5-5				
C86400	56-62	0.5-1.5	0.5-1.5	34-42	0.4-2	1		0.5-1.5	0.1-1.5				
C86500	55-60	1	0.4	36-42	0.4-2	1		0.5-1.5	0.1-1.5				
C86550	57 Min	1	0.5	Rem.	0.7-2	1		0.5-2.5	0.1-3	0.1			
C86700	55-60	1.5	0.5-1.5	30-38	1-3	1		1-3	0.1-3.5				
C86800	53.5-57	1	0.2	Rem.	1-2.5	2.5-4		2	2.5-4				
C99700	54 Min	1	0.2	19-25	1	4-6		0.5-3	11-15				
C99750	55-61		0.5-2.5	17-23	1	5		0.25-3	17-23				